Edgetek™ ET3300-0030 RS White

Polybutylene Terephthalate

PolyOne Corporation

Message:

Edgetek[™] ET3300-0030 RS White is a Polybutylene Terephthalate (PBT) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Edgetek[™] ET3300-0030 RS White include appliances, automotive, consumer goods, engineering/industrial parts and housings. Characteristics include: Chemical Resistant Crystalline Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Good Chemical Resistance		
	High Heat Resistance		
	Semi Crystalline		
Uses	Appliance Components		
	Appliances		
	Automotive Applications		
	Consumer Applications		
	Housings		
	Industrial Applications		
	Structural Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	7310	N (D	
		MPa	ASTM D638
Tensile Strength ² (Break)	82.7	MPa MPa	ASTM D638
Tensile Strength [–] (Break) Tensile Elongation (Break)			
	82.7	МРа	ASTM D638
Tensile Elongation (Break)	82.7 3.0	MPa %	ASTM D638 ASTM D638
Tensile Elongation (Break) Flexural Modulus ³	82.7 3.0 6550	MPa % MPa	ASTM D638 ASTM D638 ASTM D790
Tensile Elongation (Break) Flexural Modulus ³ Flexural Strength ⁴	82.7 3.0 6550 138	MPa % MPa MPa	ASTM D638 ASTM D638 ASTM D790 ASTM D790
Tensile Elongation (Break) Flexural Modulus ³ Flexural Strength ⁴ Impact	82.7 3.0 6550 138 Nominal Value	MPa % MPa MPa Unit	ASTM D638 ASTM D638 ASTM D790 ASTM D790 Test Method
Tensile Elongation (Break) Flexural Modulus ³ Flexural Strength ⁴ Impact Notched Izod Impact	82.7 3.0 6550 138 Nominal Value	MPa % MPa MPa Unit	ASTM D638 ASTM D638 ASTM D790 ASTM D790 Test Method
Tensile Elongation (Break) Flexural Modulus ³ Flexural Strength ⁴ Impact Notched Izod Impact NOTE	82.7 3.0 6550 138 Nominal Value 91	MPa % MPa MPa Unit	ASTM D638 ASTM D638 ASTM D790 ASTM D790 Test Method
Tensile Elongation (Break) Flexural Modulus ³ Flexural Strength ⁴ Impact Notched Izod Impact NOTE 1.	82.7 3.0 6550 138 Nominal Value 91 5.1 mm/min	MPa % MPa MPa Unit	ASTM D638 ASTM D638 ASTM D790 ASTM D790 Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

