

Flontech® FT-905-RSH

Polytetrafluoroethylene

Guarniflon S.p.A. - Flontech Division

Message:

100% repro PTFE

General Information			
Forms	Powder, Reprocessed		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.50	g/cm ³	ASTM D4894
Water Absorption (Equilibrium)	0.020	%	Internal Method
Particle Size Distribution			Internal Method
at 10%	1.5	µm	
at 50%	6.0	µm	
at 90%	20.0	µm	
Specific Surface Area	3.0	m ² /g	ASTM D4567
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	323	°C	ASTM D4591

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

