

Tekuform C13

Acetal (POM) Copolymer
TEKUMA Kunststoff GmbH

Message:

Tekuform C13 is an Acetal (POM) Copolymer material. It is available in Europe. Primary attribute of Tekuform C13: Flame Rated.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage - Flow	2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	59.8	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	6.1	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	158	°C	ASTM D648
Melting Temperature	165	°C	DSC
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT