NEXT SIGNATURE PC EG-100

Polycarbonate

NEXT Specialty Resins, Inc.

Message:

NEXT SIGNATURE PC EG-100 is a Polycarbonate (PC) material. It is available in North America. Primary attribute of NEXT SIGNATURE PC EG-100: Halogen Free

Typical applications include:

Appliances

Electrical/Electronic Applications

| General Information | | | | |
|---|------------------------------------|--------------|-------------|--|
| Features | Halogen Free | Halogen Free | | |
| Uses | Appliance Components | | | |
| | Electrical/Electronic Applications | | | |
| Appearance | Natural Color | | | |
| Forms | Pellets | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.20 | g/cm³ | ASTM D792 | |
| Melt Mass-Flow Rate (MFR) | 3.0 | g/10 min | ASTM D1238 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Rockwell Hardness (M-Scale) | 70 | | ASTM D785 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength | 59.3 | MPa | ASTM D638 | |
| Tensile Elongation (Break) | 80 | % | ASTM D638 | |
| Flexural Modulus | 2070 | MPa | ASTM D790 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Deflection Temperature Under Load (1. MPa, Unannealed) | 8 131 | °C | ASTM D648 | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

