

# Silastic® 7-4870

Silicone  
Dow Corning Corporation

Message:

Liquid Silicone Rubber raw materials for medical device and component fabrication in the Healthcare Industry

APPLICATION

SILASTIC BioMedical Grade Liquid Silicone Rubbers (7-6830, 7-6840, Q7-4840, Q7-4850, 7-4860, 7-4870 and 7-6860) are heat-cured elastomer raw materials for use by customers fabricating medical devices, including those intended for implantation in humans for less than 30 days.

DESCRIPTION

SILASTIC BioMedical Grade Liquid Silicone Rubbers (7-6830, 7-6840, Q7-4840, Q7-4850, 7-4860, 7-4870 and 7-6860) are a series of two-part platinum-catalyzed silicone elastomers specifically designed for liquid injection molding or supported extrusion. Each elastomer is supplied as a two-part kit (Part A and Part B), equal portions (by weight) of which must be thoroughly blended together prior to use. The elastomer is thermally cured via an addition-cure (platinum-catalyzed) reaction. When blended and cured as indicated, the resulting elastomer consists of crosslinked dimethyl and methyl-vinyl siloxane copolymers and reinforcing silica.

The SILASTIC BioMedical Grade Liquid Silicone Rubbers are available in a range of nominal hardness from 30 to 60, Durometer-Shore A. The elastomers can be used without any post-cure although if necessary, this may be employed to stabilize final properties. Furthermore, the elastomers are heat stable up to 204°C (400°F), can be autoclaved, and exhibit high gas permeability compared with most thermoset elastomers and thermoplastics.

General Information			
Features	High Gas Permeability		
	Good coloring		
	High pressure heating resistance		
Uses	Medical/nursing supplies		
Agency Ratings	EP Unspecified Rating		
	ISO 10993-Part I		
	USP Class VI		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	2.7	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	66		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (200% Strain)	5.70	MPa	ASTM D412
Tensile Strength	9.50	MPa	ASTM D412
Tensile Elongation (Break)	420	%	ASTM D412
Tear Strength <sup>1</sup>	47.0	kN/m	ASTM D624
Compression Set	46	%	ASTM D395
NOTE			
1.	B mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

