

TEREZ GT3 300 H G40

Polyamide 66
TER HELL PLASTIC GMBH

Message:
PA66 Blend with partial aromatic share, 40% glass fiber content and heat stabilizer
For all kind of injection molding parts with requirements on strength

General Information				
Filler / Reinforcement		Glass Fiber,40% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
		High Strength		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	4.5	--	%	
Equilibrium, 23°C, 50% RH	1.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	13500	12500	MPa	ISO 527-2
Tensile Stress (Break)	230	--	MPa	ISO 527-2
Tensile Strain (Break)	3.0	3.0	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	248	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	238	--	°C	ISO 75-2/A
Vicat Softening Temperature	210	--	°C	ISO 306/B50
Melting Temperature ¹	260	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+14	--	ohms · cm	IEC 60093
Electric Strength	33	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112

Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (1.60 mm)	HB	--		IEC 60695-11-10, -20
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

