TABOREN PH 82 H 20

Polypropylene Homopolymer

SILON s.ro

Message:

TABOREN PH 82 H 20 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 20% mineral. It is available in Asia Pacific or Europe. Typical application: Appliances. Characteristics include: Antioxidant Homopolymer

| General Information | | | |
|---------------------------------------|--------------------------------|----------|-----------------|
| Filler / Reinforcement | Mineral,20% Filler by Weight | | |
| Additive | Antioxidant | | |
| Features | Antioxidant | | |
| | Homopolymer | | |
| | | | |
| Uses | White Goods & Small Appliances | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.04 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 14 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield) | 31.0 | MPa | ISO 527-2/1B/50 |
| Flexural Modulus | 2500 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 3.0 | kJ/m² | ISO 179/1eA |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 155 | °C | ISO 306/A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd. Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

