

PERLER® N09X2001B01

Polypropylene Homopolymer

A.D. Compound S.p.A.

Message:

PP Stabilized Homopolymer Natural 20% Mixed Mineral filled

| General Information | | | |
|---|--------------------------------------|-------------------|-------------|
| Filler / Reinforcement | Mineral filler, 20% filler by weight | | |
| Features | Homopolymer | | |
| Appearance | Natural color | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 6.0 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus | 1800 - 2200 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 2.0 - 4.0 | kJ/m ² | ISO 180/1A |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 97.5 | °C | ISO 306 |
| Heat Deflection Temperature | 60 | °C | ISO 75-2 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

