

ENVIROPLAS® ENV08-NC470

Polybutylene Terephthalate

ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, 30% Fiberglass Reinforced, Good Chemical Resistance, High Heat Resistance and Dimensional Stability, RoHS Compliant
NC470 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.
The ENV08 Series Products Are Available With Mold Release and/or UV Stabilizer.
Contact Enviroplas Regarding UL Recognized Versions Of This Product.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	High Heat Resistance		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.70	%	ASTM D955
Ash Content	30	%	ASTM D5630
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	100	MPa	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	172	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	199	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.10	%	

Rear Temperature	238 to 254	°C
Middle Temperature	243 to 266	°C
Front Temperature	249 to 271	°C
Nozzle Temperature	243 to 266	°C
Mold Temperature	65.6 to 87.8	°C
Injection Rate	Moderate	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	50 to 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

