McCann PP M20TCPP12

Polypropylene Copolymer

McCann Plastics Inc.

Message:

McCann PP M20TCPP12 is a Polypropylene Copolymer (PP Copolymer) product filled with 20% talc. It is available in North America. Applications of McCann PP M20TCPP12 include appliances, automotive and household applications. Characteristics include: Flame Rated Copolymer Good Stiffness Good UV Resistance Impact Resistant

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	UV Stabilizer		
Features	Copolymer		
	General Purpose		
	Good Flow		
	Good Impact Resistance		
	Good Stiffness		
	Good UV Resistance		
Uses	Appliances		
	Automotive Applications		
	General Purpose		
	Lawn and Garden Equipment		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3 to 1.7	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	88		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	21.4	MPa	ASTM D638
Tensile Elongation (Yield)	11	%	ASTM D638

Flexural Modulus - Tangent	1710	MPa	ASTM D790
Flexural Strength	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Gardner Impact	4.52	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	107	°C	
1.8 MPa, Unannealed	55.6	°C	
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

