# Zhongfa PA66 ST-24

# Polyamide 66

## Yuyao Zhongfa Engineering Plastics Co. Ltd.

#### Message:

Zhongfa PA66 ST-24 is a polyamide 66 (nylon 66) material. This product is available in the Asia-Pacific region and is processed by injection molding. The main characteristics of Zhongfa PA66 ST-24 are: impact resistance. Typical application areas include: Electrical/electronic applications electrical appliances Furniture Automotive Industry Sporting goods

| General Information  |                                    |          |             |  |
|--|------------------------------------|----------|-------------|--|
| Features   | Impact resistance, high            |          |             |  |
|  | Low temperature impact resistance  | e        |             |  |
|  |                                    |          |             |  |
| Uses   | Electrical/Electronic Applications |          |             |  |
|  | Electrical appliances              |          |             |  |
|  | Furniture                          |          |             |  |
|  | Application in Automobile Field    |          |             |  |
|  | Sporting goods                     |          |             |  |
|  |                                    |          |             |  |
| Forms  | Particle                           |          |             |  |
| Processing Method  | Injection molding                  |          |             |  |
| Physical   | Nominal Value                      | Unit     | Test Method |  |
| Specific Gravity   | 1.06                               | g/cm³    | ASTM D792   |  |
| Melt Mass-Flow Rate (MFR)                                  | 8.2                                | g/10 min | ASTM D1238  |  |
| Molding Shrinkage - Flow                                   | 1.5                                | %        | ASTM D955   |  |
| Mechanical   | Nominal Value                      | Unit     | Test Method |  |
| Tensile Strength   | 46.0                               | MPa      | ASTM D638   |  |
| Tensile Elongation (Break)                                 | 180                                | %        | ASTM D638   |  |
| Flexural Modulus   | 1310                               | MPa      | ASTM D790   |  |
| Flexural Strength  | 59.0                               | MPa      | ASTM D790   |  |
| Thermal  | Nominal Value                      | Unit     | Test Method |  |
| Deflection Temperature Under Load (1.8<br>MPa, Unannealed) | 62.0                               | °C       | ASTM D648   |  |
| Electrical   | Nominal Value                      | Unit     | Test Method |  |
| Volume Resistivity   | 1.0E+15                            | ohms·cm  | ASTM D257   |  |
| Additional Information                                     |                                    |          |             |  |
| Notched Izod Impact, ASTM D256: 89.6 kJ/r                  | m²                                 |          |             |  |
| Injection  | Nominal Value                      | Unit     |             |  |
| Drying Temperature   | 85.0 - 90.0                        | °C       |             |  |
|  |                                    |          |             |  |

| Drying Time            | 6.0 - 8.0   | hr  |  |
|------------------------|-------------|-----|--|
| Processing (Melt) Temp | 235 - 265   | °C  |  |
| Mold Temperature       | 60.0 - 90.0 | °C  |  |
| Injection Pressure     | 60.0 - 100  | MPa |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

