

# Axial PVC 8810

Flexible Polyvinyl Chloride

Axial Corporation

## Message:

Low gravity extrusion compound especially formulated for extruded T-moldings and other shapes where uniform flow through the die is required. Exhibits good flex whitening resistance.

General Information			
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24 - 1.28	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	78 - 84		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	16.5	MPa	ASTM D638
100% strain	8.79	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Additional Information			

Recommended Stock Temperature: 365°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

