

Shin-Etsu Elastomer KE-941U

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

KE-941 U is one of a series of easy processing, general purpose silicone rubber bases. It can be used in a variety of applications requiring finishing by molding (compression, injection, transfer).

Typical Applications

Rubber contacts.

Food packing.

Industrial packing.

Diaphragms.

General Information		
Features	Workability, good	
	General	
Uses	Diaphragm	
	Industrial application	
	Food packaging	
	General	
Processing Method	Resin transfer molding	
	Compression molding	
	Injection molding	
Physical	Nominal Value	Unit
Specific Gravity	1.12	g/cm ³
Hardness	Nominal Value	Unit
Durometer Hardness	40	
Elastomers	Nominal Value	Unit
Tensile Strength	7.34	MPa
Tensile Elongation (Break)	390	%
Tear Strength ¹	9.81	kN/m
Compression Set (149°C, 22 hr)	10	%
Thermoset	Nominal Value	Unit
Post Cure Time (200°C)	4.0	hr
Additional Information	Nominal Value	Unit
Cure Agent	DBPH	
Press / Post Cure: Post		
NOTE		
1.	B mould	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

