

SEQUEL® 1718-PUV

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Sequel 1718-PUV thermoplastic polyolefin is designed for painted automotive exterior applications that require dimensional stability over a broad temperature range. This material exhibits excellent processability and low-temperature properties.

General Information			
Features	Good Dimensional Stability		
	Good Processability		
	Low Temperature Impact Resistance		
	Low Temperature Resistant		
	Paintable		
Uses	Automotive Applications		
	Automotive Exterior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (4.00 mm)	1600	MPa	ISO 178

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT