## Sylvin 6231-90 Yellow 4202

## Polyvinyl Chloride

Sylvin Technologies Incorporated

## Message:

Sylvin 6231-90 Yellow 4202 Is A Vinyl Compound Formulated For Extruded Yarn Coating Applications That Require Superior Flammability And Chemical Resistance.

| General Information        |                             |       |             |
|----------------------------|-----------------------------|-------|-------------|
| Features                   | Good chemical resistance    |       |             |
|                            | Flame retardancy            |       |             |
|                            |                             |       |             |
| Uses                       | Wire and cable applications |       |             |
|                            | Coating application         |       |             |
| Appearance                 | Yellow                      |       |             |
| Processing Method          | Extrusion                   |       |             |
|                            | Extrusion coating           |       |             |
|                            |                             |       |             |
| Physical                   | Nominal Value               | Unit  | Test Method |
| Specific Gravity           | 1.37                        | g/cm³ | ASTM D792   |
| Hardness                   | Nominal Value               | Unit  | Test Method |
| Durometer Hardness         |                             |       | ASTM D2240  |
| Shaw A                     | 90                          |       | ASTM D2240  |
| Shaw A, 10 seconds         | 90                          |       | ASTM D2240  |
| Mechanical                 | Nominal Value               | Unit  | Test Method |
| Tensile Strength (Break)   | 20.7                        | МРа   | ASTM D638   |
| Tensile Elongation (Break) | 330                         | %     | ASTM D638   |
| Elastomers                 | Nominal Value               | Unit  | Test Method |
| Tear Strength              | 105                         | kN/m  | ASTM D624   |
| Thermal                    | Nominal Value               | Unit  | Test Method |
| Continuous Use Temperature | 105                         | °C    | ASTM D794   |
| Brittleness Temperature    | -10.0                       | °C    | ASTM D746   |
| Melting Temperature        | 177 - 188                   | °C    |             |
| Flammability               | Nominal Value               | Unit  | Test Method |
| Oxygen Index               | 32                          | %     | ASTM D2863  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

