

Pibiflex® 3560

Thermoplastic Copolyester Elastomer

SO.F.TER. SPA

Message:

Pibiflex® 3560 is a Thermoplastic Copolyester Elastomer (TPC-ET) material. It is available in Europe, Latin America, or North America for injection molding. Primary attribute of Pibiflex® 3560: REACH Compliant.

General Information			
Features	General Purpose		
Uses	General Purpose		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Melt Volume-Flow Rate (MVR) (220°C/2.16 kg)	25.0	cm ³ /10min	ASTM D1238
Water Absorption (23°C, 24 hr)	0.90	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	35		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	18.0	MPa	ASTM D638
Tensile Elongation (Break)	850	%	ASTM D638
Flexural Modulus	55.0	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	60.0	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	195	°C	ASTM D3417
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
23°C	1.0E+13	ohms · cm	
100°C	1.0E+11	ohms · cm	
Dielectric Strength (2.00 mm)	17	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	4.30		
100 kHz	4.25		
Dissipation Factor			ASTM D150

1 kHz	6.0E-3		
100 kHz	0.015		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	20	%	ASTM D2863
Additional Information	Nominal Value	Unit	Test Method
Fatigue Resistance	0.1/300	kCycles	ASTM D1052
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	3.0	hr	
Rear Temperature	180	°C	
Middle Temperature	210	°C	
Front Temperature	220	°C	
Mold Temperature	40.0 to 60.0	°C	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

