

Laticonther 62 CPG/500

Polyamide 6

LATI S.p.A.

Message:

High thermal conductivity product based on Polyamide 6 (PA6).
Special filler. Glass fibres.

General Information			
Filler / Reinforcement	Filler		
Features	Thermally Conductive		
Physical	Nominal Value	Unit	Test Method
Density	1.91	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.45 to 0.70	%	
Flow : 2.00 mm	0.35 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	8500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	120	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	195	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B50
Thermal Conductivity	1.2	W/m/K	Internal Method
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate		
NOTE			
1.	60 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT