

YUNCON® N270

Acetal (POM) Copolymer

YunNan YunTianHua Co., Ltd.

Message:

High-flow grade, with minimized mold deposit

General Information			
Features	Acid Resistant Bacteria Resistant Copolymer Fatigue Resistant Good Abrasion Resistance Good Chemical Resistance Good Dimensional Stability Good Electrical Properties High Flow High Hardness Low Friction Low Warpage Solvent Resistant		
Uses	Bottles Fasteners		
Agency Ratings	DMF Unspecified Rating EN 71-3 FDA Unspecified Rating NSF Unspecified Rating UL Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	27	g/10 min	ISO 1133
Water Absorption (23°C, 24 hr)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2

Tensile Stress (Yield)	62.0	MPa	ISO 527-2
Tensile Strain (Break)	25	%	ISO 527-2
Flexural Modulus	2550	MPa	ISO 178
Flexural Stress	89.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.5	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	98.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	160 to 180	°C	
Middle Temperature	170 to 200	°C	
Front Temperature	190 to 210	°C	
Nozzle Temperature	180 to 210	°C	
Processing (Melt) Temp	180 to 210	°C	
Mold Temperature	60.0 to 90.0	°C	
Injection Pressure	50.0 to 100	MPa	
Holding Pressure	0.00 to 80.0	MPa	
Back Pressure	0.00 to 0.500	MPa	
Screw Speed	50 to 120	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

