# THERMOLAST® K TC5PCN (Series: AD/PA/CS)

### Thermoplastic Elastomer

#### KRAIBURG TPE

#### Message:

The AD/PA/CS Series is your material solution for applications with excellent adhesion to PA as well as outstanding compression set. The compounds are available in natural and black colors. Typical applications Fastenings Grommets Membranes Seals Material advantages Easy coloring (compounds in natural colors) Excellent compression set Insert molding possible UL 94 HB listed

General Information			
UL YellowCard	E214822-586867		
Features	Good Adhesion		
	Good Colorability		
Uses	Fasteners		
	Grommets		
	Membranes		
	Seals		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	47		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (Yield)	4.00	MPa	ISO 37
Tensile Elongation <sup>2</sup> (Break)	350	%	ISO 37
Tear Strength <sup>3</sup>	12	kN/m	ISO 34-1
Compression Set <sup>4</sup>			ISO 815
23°C, 72 hr	16	%	
70°C, 24 hr	32	%	
100°C, 24 hr	45	%	
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94
Additional Information	Nominal Value	Unit	Test Method

Adhesion to PA6	11.5	kN/m	Renault D41/1916	
Adhesion to PA66	7.0	kN/m	Renault D41/1916	
Injection	Nominal Value	Unit		
Drying Temperature	60.0 to 80.0	°C		
Drying Time	2.0 to 4.0	hr		
Rear Temperature	230 to 245	°C		
Middle Temperature	250 to 260	°C		
Front Temperature	260 to 270	°C		
Mold Temperature	40.0 to 60.0	°C		
Injection Pressure	20.0 to 100	MPa		
Back Pressure	2.00 to 10.0	MPa		
NOTE				
1.	Type S2, 200 mm/min			
2.	Type S2, 200 mm/min	Type S2, 200 mm/min		
3.	Method Bb, Angle (Nicked)	Method Bb, Angle (Nicked)		
4.	Method A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

