

# Manner Flexible PVC M6113

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

Recommended Applications: 80°C General Purpose Non Lead Injection Molding Compound for Appliance and Automotive Harness Components. Meets requirements to Ford Motor Company Specification ESB-M4D317A Type III and meets Chrysler Corporation Specification MC-DC226.

General Information			
Features	General Purpose		
	Low (to None) Lead Content		
Uses	Appliance Components		
	Automotive Applications		
	General Purpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30 to 1.34	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	62 to 68		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	10.3	MPa	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Additional Information	Nominal Value	Unit	
Stock Temperature - Recommended Molding	171	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT