

TAIRIPRO KP03B

Polypropylene Impact Copolymer

Formosa Plastics Corporation

Message:

FCFC PP resin KP03B meets the requirements of RoHS and the certificates of environmental protection.

General Information			
UL YellowCard	E162823-100605206		
Features	Impact copolymer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
UL File Number	E162823		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	1.4 - 1.8	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	25.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 100	%	ASTM D638
Flexural Modulus (23°C)	1420	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact			ASTM D256
-20°C, 3.18 mm	36	J/m	ASTM D256
23°C, 3.18 mm	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.35 mm)	115	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, ALL)	HB		UL 94
Injection	Nominal Value	Unit	
Mold Temperature	30.0 - 50.0	°C	
Injection Pressure	2.94 - 5.88	MPa	
Injection instructions			
Screw Temp: 180-230 °C			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

