

Durethan® BKV 25 FN27 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 25 % glass, injection molding, halogen free flame retardant

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 25% filler by weight		
Additive		Flame retardancy		
Features		Halogen-free		
		Flame retardancy		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.35	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	0.70	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.20	--	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	0.60	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.20	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	7.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.1	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5300	2200	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	85.0	38.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	30	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5000	3000	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	125	65.0	MPa	ISO 178/A
23°C ⁶	135	70.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.5	%	ISO 178/A
ISO Shortname	PA6, GFHR, 12-050, G25, ISO1043, PA G FR (30)			ISO 1874
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method

Charpy Unnotched Impact Strength (23°C)	35	70	kJ/m ²	ISO 179/1eU
Unnotched Izod Impact Strength (23°C)	25	55	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	205	--	°C	ISO 75-2/B
1.8 MPa, not annealed	155	--	°C	ISO 75-2/A
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 1	--		UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	V-2	--		UL 94
1.50 mm	V-2	--		UL 94
3.00 mm	V-2	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.750 mm	960	--	°C	IEC 60695-2-12
1.50 mm	960	--	°C	IEC 60695-2-12
3.00 mm	960	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	750	--	°C	IEC 60695-2-13
1.50 mm	750	--	°C	IEC 60695-2-13
3.00 mm	750	--	°C	IEC 60695-2-13
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	250 - 270		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

