# EverGlide® SG5708T

### Polyetheretherketone

#### Polymer Dynamix

#### Message:

~

....

...

Lubricated PEEK Features: Excellent Chemical Resistance Low Temperature Flexibility Excellent Processability Applications: Automotive Aerospace Industrial

General Information			
Features	Good Chemical Resistance Good Flexibility Good Processability		
Uses	Aerospace Applications		
	Automotive Applications		
	Industrial Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	48.3	MPa	
Break	34.5	MPa	
Tensile Elongation			ASTM D638
Yield	9.0 to 10	%	
Break	> 50	%	
Flexural Modulus	2590	MPa	ASTM D790

Notched lzod Impact (23°C, 3.18 mm)

Flexural Strength

Impact

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

96.5

64

Nominal Value

#### Recommended distributors for this material

MPa

Unit

J/m

ASTM D790

Test Method

ASTM D256

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

