Topilene® J801R

Polypropylene Homopolymer

Hyosung Corporation

Message:

Characteristics:

High Stiffness

Long term heat resistance, UL 746B

Applications:

Toaster

Coffee maker

Steam iron

General Information			
UL YellowCard	E163907-224780		
Features	Good Stiffness		
	High Heat Resistance		
	Homopolymer		
Uses	Appliances		
	Electrical/Electronic Applications		
	Household Goods		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	18	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	34	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

