

FERREX® GPP40CC83WH

Polypropylene Homopolymer

Ferro Corporation

Message:

FERREX® GPP40CC83WH is a polypropylene homopolymer (PP Homopoly) material, and its filler is 40% calcium carbonate filler. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

FERREX® The main features of the GPP40CC83WH are:

high gloss

Homopolymer

General Information			
Filler / Reinforcement	Calcium carbonate filler, 40% filler by weight		
Features	Highlight		
	Homopolymer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.4	%	ASTM D955
Transverse flow	1.8	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	24.1	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	15	%	ASTM D638
Flexural Modulus			ASTM D790
1% secant: 23°C	2080	MPa	ASTM D790
Tangent: 23°C	2450	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	41.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1100	J/m	ASTM D256
Dart Drop Impact	21.7	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	96.1	°C	ASTM D648
1.8 MPa, not annealed	68.3	°C	ASTM D648
Additional Information			
Filler Content, ASTM D2584: 40%			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

