

# ExxonMobil™ LDPE LD 380BA Wire & Cable

Low Density Polyethylene Resin  
ExxonMobil Chemical

Message:

LD 380BA is a non-stable low-density polyethylene, specially developed for the production of low-voltage cable insulators using two-step silane crosslinking technology. Insufficient amounts of antioxidants and copper inhibitors should be added to make the product meet specific anti-aging requirements.

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.8	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	53		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	17.0	MPa	ASTM D638
Fracture	13.0	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	13	%	ASTM D638
Fracture	110	%	ASTM D638
Flexural Modulus - 1% Secant	440	MPa	ASTM D790
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms·cm	ASTM D257
Dielectric Constant (60 Hz)	2.30		ASTM D150
Dissipation Factor (60 Hz)	< 4.0E-4		ASTM D150
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT