OxyVinyIs® 226F

Polyvinyl Chloride Homopolymer

OxyVinyls, LP

Message:

OxyVinyls® 226F is a Polyvinyl Chloride Homopolymer (PVC Homopolymer) product. It can be processed by film extrusion, injection molding, profile extrusion, or sheet extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of OxyVinyls® 226F include film, sheet and wire & cable.

Characteristics include:

Clarity

Good Flexibility

High Purity

Homopolymer

General Information		
Features	Clean/High Purity	
	Good Colorability	
	Good Flexibility	
	High Clarity	
	Homopolymer	
	Low Gel	
Uses	Film	
	Profiles	
	Sheet	
	Wire & Cable Applications	
Appearance	White	
Forms	Powder	
Processing Method	Film Extrusion	
	Injection Molding	
	Profile Extrusion	
	Sheet Extrusion	

Physical	Nominal Value	Unit	Test Method
Apparent Density	0.48 to 0.57	g/cm³	Internal Method
K-Value	66.0 to 67.0		
Color - CIELab b*-value	0.30 to 0.90		Internal Method
Contamination	< 12	number/kg	Internal Method
Gel Content - 4' mill results	< 10.0		Internal Method
Inherent Viscosity	0.93 to 0.97	dl/g	Internal Method
Particle Size			Malvern
% Retained on Pan	< 4.00	%	

% Retained on 200 mesh	< 18.0	%	
% Retained on 40 mesh	< 0.200	%	
% Retained on 60 mesh	< 6.00	%	
Relative Viscosity	2.20 to 2.28		
CAS Number	9002-86-2		
Flow Time	< 12.0	sec	Internal Method
Porosity	0.300 to 0.360	cm³/g	Internal Method
Powder Mix Time	4.2 to 5.8	min	Internal Method
Residual Monomer	< 1	ppm	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

