

LEXAN™ HPH4504H resin

Polyphthalate Carbonate

SABIC Innovative Plastics

Message:

High heat specialty polycarbonate with enhanced autoclavability. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 of USP Class VI). EtO, steam, gamma and e-beam sterilizable.

General Information			
Features	Electron beam disinfection		
	Radiation disinfection		
	Pressure cooker disinfection		
	Ethylene oxide disinfection		
	High pressure heating resistance		
	Heat resistance, high		
	Biocompatibility		
	Disinfect with steam		
Uses	Drug		
	Medical/nursing supplies		
Agency Ratings	ISO 10993		
	USP Class VI		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792, ISO 1183
--	1.19	g/cm ³	ASTM D792
Specific Volume	0.830	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR)			ISO 1133
300°C/1.2 kg	3.00	cm ³ /10min	ISO 1133
330°C/2.16 kg	12.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.70 - 0.80	%	Internal method
Water Absorption			
24 hr	0.16	%	ASTM D570
Saturated, 23°C	0.16	%	ISO 62
Equilibrium, 23°C, 50% RH	0.35	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785

Class m	85		ASTM D785
Class r	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2090	MPa	ASTM D638
--	2260	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	65.5	MPa	ASTM D638
Yield	65.0	MPa	ISO 527-2/5, ISO 527-2/50
Fracture ³	71.7	MPa	ASTM D638
Fracture	65.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	7.0	%	ISO 527-2/50
Fracture ⁵	120	%	ASTM D638
Fracture	7.0	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2030	MPa	ASTM D790
-- ⁷	2130	MPa	ISO 178
Flexural Stress			
--	66.0	MPa	ISO 178
Yield, 50.0mm span ⁸	95.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	15	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	140	J/m	ASTM D256
23°C	640	J/m	ASTM D256
-30°C ¹⁰	11	kJ/m ²	ISO 180/1A
23°C ¹¹	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	3200	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Total Energy)	73.0	J	ASTM D3763
Dart Drop Impact (23°C)	149	J	ASTM D3029
Tensile Impact Strength ¹²	578	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	143	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹³	132	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	160	°C	ASTM D1525 ¹⁴
--	154	°C	ISO 306/B50
--	155	°C	ISO 306/B120

Linear thermal expansion coefficient			
Flow: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flow: -40 to 95°C	9.2E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Specific Heat	1260	J/kg/°C	ASTM C351
Thermal Conductivity	0.21	W/m/K	ASTM C177
RTI Elec	125	°C	UL 746
RTI Imp	125	°C	UL 746
RTI	125	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 2.6E+17	ohms · cm	ASTM D257
Dielectric Strength (3.20 mm, in Air)	20	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
50 Hz	3.15		ASTM D150
60 Hz	3.15		ASTM D150
1 MHz	3.00		ASTM D150
Dissipation Factor			ASTM D150
50 Hz	1.2E-3		ASTM D150
60 Hz	1.2E-3		ASTM D150
100 Hz	0.024		ASTM D150
Comparative Tracking Index (CTI)	PLC 3		UL 746
High Amp Arc Ignition (HAI)	PLC 4		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.47 mm)	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.600		ASTM D542
Transmittance (2540 µm)	85.0	%	ASTM D1003
Haze (2540 µm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	316 - 338	°C	
Middle Temperature	327 - 349	°C	
Front Temperature	338 - 360	°C	
Nozzle Temperature	332 - 354	°C	
Processing (Melt) Temp	338 - 360	°C	
Mold Temperature	82.2 - 116	°C	

Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

1.	5.0 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	Type S
13.	80*10*4 mm
14.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

