

YUPLENE® HX3300H

Polypropylene Homopolymer

SK Global Chemical

Message:

YUPLENE HX3300H is a high crystalline polypropylene homopolymer designed for injection molding applications. YUPLENE HX3300H has excellent properties in stiffness, flow, heat resistance and good dimensional stability. YUPLENE HX3300H can be used for auto parts, household articles, electric appliances and various containers. YUPLENE HX3300H can reduce various injection problems such as surface trouble, shrink, warpage etc. and reduce the cycle time of injection molding due to rapid crystallization. Especially, HX3300H has excellent long-term thermal stability. YUPLENE HX3300H complies with FDA regulation 21 CFR177.1520.

General Information			
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	Good Flow		
	Good Thermal Stability		
	High Heat Resistance		
	High Stiffness		
	Highly Crystalline		
	Homopolymer		
Uses	Appliances		
	Automotive Applications		
	Containers		
	Electrical Parts		
	Household Goods		
	Industrial Parts		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	38.2	MPa	ASTM D638
Tensile Elongation (Break)	< 300	%	ASTM D638
Flexural Modulus	2160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	158	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT