

Viprene™ P55D-22U-NAT

Thermoplastic Vulcanizate

Alliance Polymers & Services

Message:

Viprene™ P55D-22U-NAT is a UV and Heat Stabilized TPV (thermoplastic vulcanizate elastomer). This material can be easily procesed by extrusion or injection molding. It exhibits easy flowing characteristics.

General Information	
Additive	Heat Stabilizer
	UV Stabilizer
Features	Good Flow
	Good UV Resistance
	Heat Stabilized
Appearance	Natural Color
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm³	ISO 2781
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	55		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	10.1	MPa	
300% Strain	12.6	MPa	
Tensile Stress (Break)	16.5	MPa	ISO 37
Tensile Elongation (Break)	500	%	ISO 37
Tear Strength	100	kN/m	ISO 34-1
Compression Set (70°C, 22 hr)	43	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ASTM D746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.00 mm	HB		
1.50 mm	HB		
3.00 mm	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

