

SOFTAPLAS S 70A

Thermoplastic Elastomer

Ovation Polymers Inc.

Message:

Thermoplastic Elastomer - Excellent hydrolytic Stability and balance of properties.

General Information			
Features	Hydrolytically Stable		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/3.8 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	69 to 72		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation ¹ (Break)	> 550	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

