

Generic TEEE

Thermoplastic Elastomer, Ether-Ester

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic TEEE
This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07 - 1.36	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (23°C)	30 - 56		ASTM D2240
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 224	°C	
Mold Temperature	35.0	°C	
Injection instructions			

This data represents typical values that have been calculated from all products classified as: Generic TEEEThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

