

Plaslube® AC-80/TF/15

Acetal (POM) Copolymer

Techmer Engineered Solutions

Message:

Plaslube® AC-80/TF/15 is a polyoxymethylene (POM) copolymer product. It can be processed by injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: engineering/industrial accessories.

Features include:

ROHS certification

Lubrication

General Information			
UL YellowCard	E253782-484546		
Additive	PTFE lubricant (15%)		
Features	Lubrication		
Uses	Gear		
	Bearing		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm³	ASTM D792
Molding Shrinkage - Flow	2.0	%	ASTM D955
Water Absorption (24 hr)	0.23	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 23°C)	43.4	MPa	ASTM D638
Flexural Modulus (23°C)	2140	MPa	ASTM D790
Flexural Strength (Break, 23°C)	66.2	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
With steel-dynamic	0.16		ASTM D1894
With steel-static	0.080		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	102	°C	ASTM D648
CLTE - Flow	2.5E-5	cm/cm/°C	ASTM D696
Additional Information			
Coefficient of Friction, Static, Thrust washer, 40psi, ambient temp.: 0.08Coefficient of Friction, Dynamic, Thrust washer, 40psi, 50 ft/min, ambient temp.: 0.16Limiting PV, Thrust washer, 100 FPM, ambient temp.: 1.2E4			
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	

Drying Time	1.0 - 2.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	177 - 188	°C
Middle Temperature	188 - 199	°C
Front Temperature	182 - 193	°C
Nozzle Temperature	177 - 188	°C
Processing (Melt) Temp	188 - 204	°C
Mold Temperature	76.7 - 93.3	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.345 - 0.689	MPa

Injection instructions

Screw Speed: Medium Recommendations for Molding and Tool Conditions: Well vented Moisture Content, as received: Product is packaged at 0.2% or less. Drying not normally required. Dry at 180°F for 1 to 2 hours if necessary.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

