

Jackdaw PP EB14BL6413

Polypropylene
Jackdaw Polymers

Message:

Jackdaw PP EB14BL6413 is a Polypropylene product filled with 20% glass bead. It is available in Europe, Latin America, or North America.

General Information			
Filler / Reinforcement	Glass Bead,20% Filler by Weight		
Appearance	Blue		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792, ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Break	85.0	MPa	ISO 527-2
--	85.0	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638, ISO 527-2
Flexural Modulus	1200	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength	25	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	175	°C	ISO 1218, ASTM D2117

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT