

Chemical Resources LLD100929

Linear Low Density Polyethylene

Chemical Resources, Inc.

Message:

LLD100929 meets the requirements of the FDA regulation 21CFR 177.1520

Typical applications include housewares ,lids etc.

General Information			
Features	Food Contact Acceptable		
Uses	Household Goods		
	Lids		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Density	0.929	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	100	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	16.2	MPa	ASTM D638
Tensile Elongation (Yield)	9.3	%	ASTM D638
Flexural Modulus	524	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	50.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT