

Polifil® Nylon 625

Polyamide 66
The Plastics Group

Message:

Polifil® Nylon 625 is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in North America.

General Information		
Forms	Pellets	
Processing Method	Injection Molding	
Injection	Nominal Value	Unit
Rear Temperature	293	°C
Middle Temperature	279	°C
Front Temperature	274	°C
Nozzle Temperature	260 to 299	°C
Processing (Melt) Temp	288 to 293	°C
Injection Rate	Moderate	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT