

RTP 206 FR SP

Polyamide 66

RTP Company

Message:

Glass Fiber - Flame Retardant

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Features	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.10 - 0.40	%	ASTM D955
Moisture Content	0.20	%	
Primary Additive	35	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12400	MPa	ASTM D638
Tensile Strength	170	MPa	ASTM D638
Tensile Elongation (Yield)	2.0 - 3.0	%	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	265	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	91	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	800	J/m	ASTM D4812
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	4.0	hr	
Dew Point	-17.8	°C	
Processing (Melt) Temp	277 - 299	°C	
Mold Temperature	65.6 - 107	°C	
Injection Pressure	68.9 - 124	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

