

Huaфон JF-W-D6100

Polyurethane

Huaфон Group Co., Ltd.

Message:

Impregnation Resin with Hydrolysis Resistance

Characteristics

Hard type, 24 hours hydrolysis resistance, uniform film-forming structure, good elasticity, good anti-sticking, good color retention after hydrolyzing.

Applications

For high density technics impregnation

General Information		
Features	High Elasticity	
	High Hardness	
	Hydrolysis Resistant	
	Non-Stick	
Uses	Impregnation Applications	
Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	34 to 36	%
Viscosity (25°C)	100 to 160	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	12.0 to 15.0	MPa
Tensile Strength	> 40.0	MPa
Tensile Elongation at Break	> 200	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

