

Siveras™ LX70G25J

Liquid Crystal Polymer

Toray Resin Company

Message:

Siveras™ LX70G25J is a Liquid Crystal Polymer (LCP) product filled with 25% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Good Toughness

High Strength

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Good Toughness		
	High Strength		
Part Marking Code	>LCP-GF25<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792
Molding Shrinkage			Internal Method
Across Flow : 1.00 mm ¹	0.56	%	
Flow : 1.00 mm ²	-0.050	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	185	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	14500	MPa	ASTM D790
Flexural Strength	230	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	250	°C	ASTM D648
CLTE - Flow	9.0E-6 to 2.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value		Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.200 mm)	V-0		UL 94
NOTE			
1.	80x80x1		
2.	80x80x1mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT