

RTP EMI 330.5E FR

Polycarbonate

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
EMI 330 FR Series is a polycarbonate with stainless steel fiber concentrate in a physical bend for EMI shielding. These products are recognized by UL with a rating of 94 V-0 at 1/16 inch (1.5875mm).

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 5.0% filler by weight		
	Stainless steel fiber, 10% filler by weight		
Additive	Flame retardancy		
Features	Electromagnetic shielding (EMI)		
	Electrostatic discharge protection		
	Radio frequency shielding (RFI)		
	Flame retardancy		
Agency Ratings	MIL B-81705C		
RoHS Compliance	Contact manufacturer		
UL File Number	E84658		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40 - 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3930	MPa	ASTM D638
Tensile Strength	71.7	MPa	ASTM D638
Tensile Elongation (Break)	7.5	%	ASTM D638
Flexural Modulus	3590	MPa	ASTM D790
Flexural Strength	109	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	69	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	850	J/m	ASTM D4812

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	138	°C	ASTM D648
RTI Elec (1.59 mm)	75.0	°C	UL 746
RTI Imp (1.59 mm)	75.0	°C	UL 746
RTI (1.59 mm)	75.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4	ohms	ASTM D257
Volume Resistivity	10	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, ALL)	V-0		UL 94
Additional Information			
Molding Shrinkage, ASTM D955, 3.175mm: 4-6mm/mShielding Effectiveness, ASTM D4935: 40+ dBStatic Decay, FTMS-4046.1, Mil B-81705C: <2.0 seconds			
Injection	Nominal Value	Unit	
Rear Temperature	288 - 343	°C	
Middle Temperature	288 - 343	°C	
Front Temperature	288 - 343	°C	
Mold Temperature	65.6 - 121	°C	
Injection Pressure	68.9 - 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

