

PRL TP-FRHG30

Polybutylene Terephthalate

Polymer Resources Ltd.

Message:

PRL TP-FRHG30 is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

RoHS Compliant

Flame Retardant

Good Aesthetics

Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Surface Finish		
	High Heat Resistance		
	Self Extinguishing		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	1.0 to 5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	117	MPa	
Break, 3.18 mm	117	MPa	
Flexural Modulus (3.18 mm)	7580	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	179	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	202	°C	
1.8 MPa, Unannealed, 3.18 mm	188	°C	
Injection	Nominal Value	Unit	
Drying Temperature	116 to 121	°C	

Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	238 to 254	°C
Middle Temperature	243 to 260	°C
Front Temperature	249 to 266	°C
Processing (Melt) Temp	232 to 260	°C
Mold Temperature	71.1 to 87.8	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

