

HiFill FR® PA6/6 GF25 FR-N IM3

Polyamide 66
Techmer Engineered Solutions

Message:

HiFill FR® PA6/6 GF25 FR-N IM3 is a Polyamide 66 (Nylon 66) product filled with 25% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

- Flame Rated
- Flame Retardant
- Impact Modified
- Impact Resistant

General Information			
UL YellowCard	E253782-101773885		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Additive	Impact Modifier		
Features	Flame Retardant		
	High Impact Resistance		
Appearance	Colors Available		
	Red		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.95	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	94		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	154	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	80	J/m	
23°C	120	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	252	°C	ASTM D648

CLTE - Flow	3.6E-5	cm/cm/°C	ASTM D696
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength ¹	20	kV/mm	ASTM D149
Comparative Tracking Index	> 550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
2.00 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	> 6.0	hr	
Rear Temperature	254 to 277	°C	
Middle Temperature	254 to 277	°C	
Front Temperature	254 to 277	°C	
Processing (Melt) Temp	249 to 271	°C	
Mold Temperature	65.6 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

