ESENTTIA 30R40CD

Polypropylene Random Copolymer

Polipropileno del Caribe S.A.

Message:

Characteristics: High melt flow rate control reologhy Random copolymer polypropylene with very good optical properties and easy mold filling; fast cycle time; good impact resistance; with clarify and mold release additives.

Recommended for: High clarity and good impact resistance injection molding storing boxes (big storage containers); thin walled injection molding package and general purpose applications where clarity is important.

| General Information | | | |
|--|------------------------------------|----------|-------------|
| Additive | Clarifier | | |
| | Mold Release | | |
| | | | |
| Features | Controlled Rheology | | |
| | Fast Molding Cycle | | |
| | Food Contact Acceptable | | |
| | General Purpose | | |
| | Good Impact Resistance | | |
| | Good Mold Release | | |
| | High Clarity | | |
| | High Flow | | |
| | Opticals | | |
| | Random Copolymer | | |
| Uses | Containers | | |
| | General Purpose | | |
| | Thin-walled Packaging | | |
| Agency Ratings | EC 1907/2006 (REACH) | | |
| | EC 1935/2004 | | |
| | EC 2023/2006 | | |
| | EU 10/2011 | | |
| | FDA 21 CFR 177.1520(a)(3)(i)(c)(1) | | |
| | FDA 21 CFR 177.1520(b) | | |
| | FDA 21 CFR 177.1520(c) 3.1a | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 | | | |
| kg) | 30 | g/10 min | ASTM D1238 |

| Mechanical | Nominal Value | Unit | Test Method |
|--|--------------------|------|-------------|
| Tensile Strength ² (Yield, 3.20 mm, Injection Molded) | 26.2 | MPa | ASTM D638 |
| Tensile Elongation ³ (Yield, 3.20 mm, Injection Molded) | 15 | % | ASTM D638 |
| Flexural Modulus - 1% Secant ⁴ (3.20 mm, Injection Molded) | 931 | MPa | ASTM D790A |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.20 mm, Injection Molded) | 75 | J/m | ASTM D256A |
| Gardner Impact ⁵ (23°C, 3.20 mm, Injection Molded) | 33.9 | L | ASTM D5420 |
| NOTE | | | |
| 1. | Procedure B | | |
| 2. | Type I, 50 mm/min | | |
| 3. | Type I, 50 mm/min | | |
| 4. | Type I, 1.3 mm/min | | |
| 5. | Method A | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

