

KumhoSunny ABS 745

Acrylonitrile Butadiene Styrene
Shanghai KumhoSunny Plastics Co., Ltd.

Message:

ABS745 is Injection grade ABS resin with high impact property and high strength. ABS745 is mainly used in sound, kitchen facilities, furniture, weeding machine ,etc.

General Information			
Features	High Impact Resistance		
	High Strength		
Uses	Furniture		
	Kitchenware		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	42.0	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	2000	MPa	ASTM D790
Flexural Strength	60.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	83.0	°C	ASTM D648
Vicat Softening Temperature	94.0	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 90.0	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	190 to 200	°C
Middle Temperature	210 to 220	°C
Front Temperature	220 to 230	°C
Nozzle Temperature	215 to 225	°C
Processing (Melt) Temp	200 to 230	°C
Mold Temperature	50.0 to 80.0	°C
Back Pressure	1.00 to 5.00	MPa
Screw Speed	30 to 60	rpm

NOTE

1. Rate B (120°C/h)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

