

# FERREX® GPP20CF69UL-WH

Polypropylene  
Ferro Corporation

Message:

FERREX® GPP20CF69UL-WH is a Polypropylene material filled with 20% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of FERREX® GPP20CF69UL-WH are:

Flame Rated

Good Processability

High Gloss

Homopolymer

Typical applications include:

Appliances

Handles

Housings

General Information			
Filler / Reinforcement	Calcium Carbonate,20% Filler by Weight		
Features	Good Processability		
	High Gloss		
	Homopolymer		
Uses	Appliances		
	Handles		
	Housings		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	73		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.3	MPa	ASTM D638
Tensile Elongation (Break)	55	%	ASTM D638
Flexural Modulus	1690	MPa	ASTM D790
Flexural Strength (Yield)	43.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	36	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1200	J/m	ASTM D256

Gardner Impact	14.7	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	105	°C	
1.8 MPa, Unannealed	57.8	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	199 to 204	°C	
Middle Temperature	204 to 210	°C	
Front Temperature	210 to 216	°C	
Nozzle Temperature	216 to 221	°C	
Mold Temperature	46.1 to 60.0	°C	
Back Pressure	0.138 to 0.345	MPa	
Screw Speed	100 to 150	rpm	
Clamp Tonnage	2.8 to 4.1	kN/cm <sup>2</sup>	
Screw L/D Ratio	20.0:1.0		
Screw Compression Ratio	2.0:1.0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

