

Formolene FORMAX® L71709A

Linear Low Density Polyethylene
Formosa Plastics Corporation, U.S.A.

Message:

Formolene FORMAX® L7 is a high strength linear low density hexene copolymer polyethylene made using a gas-phase process. Film mechanical properties are significantly improved compared to competitive super hexene LLDPE film resins. Formolene FORMAX® L7 is formulated with slip and antiblock for use in high performance film applications offering excellent extrusion processing and outstanding impact strength and tear resistance. Films exhibit good optical properties. Formolene FORMAX® L7 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

- Industrial Packaging
- Industrial Liners
- Coextrusion
- Can Liners
- Consumer Trash Bags

General Information			
Additive	High Antiblock (7000 ppm) 2		
Features	Copolymer		
	Food Contact Acceptable		
	Good Tear Strength		
	Hexene Comonomer		
	High Antiblocking		
	High Strength		
	Opticals		
Uses	Bags		
	Industrial Applications		
	Liners		
	Packaging		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Coextrusion		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.917	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.90	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method

Film Thickness - Tested	25	μm	
Tensile Strength			ASTM D882
MD : Yield,25 μm, Blown Film	11.4	MPa	
TD : Yield,25 μm, Blown Film	11.3	MPa	
MD : Break, 25 μm,Blown Film	39.2	MPa	
TD : Break, 25 μm,Blown Film	29.6	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 μm,Blown Film	700	%	
TD : Break, 25 μm,Blown Film	870	%	
Dart Drop Impact (25 μm, Blown Film)	410	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 25 μm, Blown Film	380	g	
TD : 25 μm, Blown Film	710	g	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

