

POLYVIN® PVC 6820

Polyvinyl Chloride

A. Schulman Inc.

Message:

GP PVC 65A Extrusion UV

General Information	
---------------------	--

Features	General Purpose
	Good UV Resistance

Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	10.0	MPa	ASTM D638
Tensile Elongation ² (Break)	280	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	32.0	kN/m	ASTM D1004

NOTE	
------	--

1.	500 mm/min
2.	500 mm/min
3.	50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material
--

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT