Enviramid® N2315THL BK

Polyamide 6

Ravago Manufacturing Americas, LLC

Message:

Nylon 6, 15% Glass Filled, Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Impact Modifier		
Recycled Content	Yes		
Features	Impact Modified		
RoHS Compliance	RoHS Compliant		
UL File Number	E157012		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm³	ISO 1183
Molding Shrinkage - Flow (3.18 mm)	0.50 to 0.80	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	70.0	МРа	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	3200	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	4.0	kJ/m²	ISO 180

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

