

TAROMID A 260 S

Polyamide 66/6 Copolymer

Taro Plast S.p.A.

Message:

Polyamide 66/6 medium viscosity, high flow, good processing and easy release, low post shrinkage and better dimensional stability, short cycles, high rigidity.
Available: natural and colored dry blend (DB).

General Information			
Additive	Mold Release		
Features	Fast Molding Cycle		
	Good Dimensional Stability		
	Good Mold Release		
	Good Processability		
	High Flow		
	High Rigidity		
	Low Shrinkage		
	Medium Viscosity		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13 to 1.14	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/1.2 kg)	38	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	1.6 to 2.0	%	
Across Flow	1.6 to 2.0	%	
Water Absorption			
23°C, 24 hr	1.2	%	ASTM D570, ISO 62
Saturation	7.4	%	ASTM D570
Saturation, 23°C	7.4	%	ISO 62
Granule Humidity	< 0.15	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ASTM D638, ISO 527-2
Tensile Strength			ASTM D638, ISO 527-2
Yield	82.0	MPa	
Break	80.0	MPa	
Tensile Elongation (Break)	50	%	ASTM D638, ISO 527-2

Flexural Modulus	3100	MPa	ASTM D790, ISO 178
Flexural Stress			
-- ¹	120	MPa	ISO 178
Break	120	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ² (23°C)	3.8	kJ/m ²	ASTM D256, ISO 179
Charpy Unnotched Impact Strength ³			
--	> 300	kJ/m ²	ASTM D256
23°C	> 300	kJ/m ²	ISO 179
Notched Izod Impact			ISO 180, ASTM D256
-20°C, 3.20 mm	30	J/m	
23°C, 3.20 mm	40	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	85.0	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature			IEC 60216
-- ⁴	90.0	°C	
-- ⁵	120	°C	
Vicat Softening Temperature			
--	248	°C	ASTM D1525, ISO 306/A50 6 ⁶
--	235	°C	ASTM D1525, ISO 306/B50 7 ⁷
Ball Pressure Test (165°C)	Pass		VDE 0470
Melting Temperature	256	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	8.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	9.0E+15	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	24	kV/mm	ASTM D149
Comparative Tracking Index			IEC 60112
Solution A	> 600	V	
Solution B	600	V	
Flammability	Nominal Value	Unit	Test Method
Burning Rate (2.00 mm)	< 100	mm/min	FMVSS 302
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Ignition Temperature (1.00 mm)	850	°C	IEC 60695-2-13
Oxygen Index	24	%	ASTM D2863
Injection	Nominal Value	Unit	
Processing (Melt) Temp	250 to 280	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Rate	Moderate		
NOTE			
1.	Yield		

2.	6x4x50 mm
3.	6x4x50 mm
4.	20000 hrs
5.	Short Term
6.	Rate A (50°C/h), Loading 1 (10 N)
7.	Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

