Electrafil® HDPE 12009

High Density Polyethylene

Techmer Engineered Solutions

Message:

Electrafil® HDPE 12009 is a High Density Polyethylene product filled with filler. It can be processed by extrusion and is available in North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Filler		
Features	Antistatic		
Appearance	Colors Available		
	Natural Color		
	Off-White		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.968	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	3.0	%	ASTM D955
Water Absorption (24 hr)	0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	35		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	20.0	МРа	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	689	МРа	ASTM D790
Flexural Strength	24.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	121	°C	
1.8 MPa, Unannealed	60.0	°C	
CLTE - Flow	1.4E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9 to 1.0E+11	ohms	ASTM D257
Volume Resistivity	1.0E+9 to 1.0E+11	ohms·cm	ASTM D257
Static Decay	< 2.0	sec	MIL B-81705C
Flammability	Nominal Value	Unit	Test Method

Flame Rating HB UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

